


样品名称: HFC	SOP名称: 88888. sop	测量时间: 2026/7/23 9:19:19	样品编号: 2601700
测试者: TK	背景采样时间: 5 秒	单次采样时间: 5 秒	结果类型: 体积(V)

样品材质: 8888	样品材质折射率: 2.6	样品材质吸收率: 0.1	分散介质: 水
分散介质折射率: 1.333	分析模式: 通用模式	遮光率(%): 7.03	分析范围(μm): 0.1 ~ 1000

D10 (μm): 1.284	D25 (μm): 1.910	D50 (μm): 3.083	D75 (μm): 6.341
D90 (μm): 17.382	D97 (μm): 29.907	D(3,2) (μm): 2.632	D(4,3) (μm): 6.412
Span: 5.222	体积比表面积(sq. m/c. c.): 2.280	重量比表面积(m ² /kg): 2279.864	残差(%): 0.027



粒径(μm)	微分(%)	累积(%)	粒径(μm)	微分(%)	累积(%)	粒径(μm)	微分(%)	累积(%)	粒径(μm)	微分(%)	累积(%)
0.100			1.075	3.57	5.67	11.565	2.27	81.91	124.370	0.00	100.00
0.127	0.00	0.00	1.364	5.79	11.46	14.666	4.83	86.74	157.715	0.00	100.00
0.161	0.00	0.00	1.729	8.60	20.06	18.598	4.55	91.30	200.000	0.00	100.00
0.204	0.00	0.00	2.193	11.79	31.85	23.584	2.80	94.10	253.620	0.00	100.00
0.259	0.00	0.00	2.781	13.27	45.12	29.907	2.90	97.00	321.620	0.00	100.00
0.328	0.00	0.00	3.527	11.26	56.38	37.925	2.31	99.31	407.850	0.00	100.00
0.416	0.00	0.00	4.472	8.83	65.20	48.094	0.69	100.00	517.200	0.00	100.00
0.527	0.00	0.00	5.671	7.48	72.69	60.988	0.00	100.00	655.870	0.00	100.00
0.669	0.40	0.40	7.192	4.93	77.61	77.339	0.00	100.00	831.710	0.00	100.00
0.848	1.70	2.10	9.120	2.03	79.64	98.075	0.00	100.00	1000.000	0.00	100.00